



Ferritringe

Material 43

Typ	$\Sigma \ell/A(\text{cm}^{-1})$	$\ell_e(\text{cm})$	$A_e(\text{cm}^2)$	$V_e(\text{cm}^3)$	$A_L(\text{nH})\pm 25\%$
FT-23-43	63.8	1.30	0.020	0.027	158
FT-37-43	28.6	2.07	0.072	0.15	350
FT-50-43	22.9	2.95	0.129	0.38	440
FT-82-43	21.3	5.2	0.243	1.26	470
FT-114-43	19.8	7.3	0.37	2.70	510
FT-140-43	11.2	8.9	0.79	7.0	885
FT-240-43	9.2	14.5	1.58	22.8	1075

Material 61

Typ	$\Sigma \ell/A(\text{cm}^{-1})$	$\ell_e(\text{cm})$	$A_e(\text{cm}^2)$	$V_e(\text{cm}^3)$	$A_L(\text{nH})\pm 25\%$
FT-23-61	63.8	1.30	0.020	0.027	25
FT-37-61	28.6	2.07	0.072	0.15	55
FT-50-61	22.9	2.95	0.129	0.38	69
FT-82-61	21.3	5.2	0.243	1.26	75
FT-114-61	19.8	7.3	0.37	2.70	80
FT-140-61	11.2	8.9	0.79	7.0	140
FT-240-61	9.2	14.5	1.58	22.8	170

Material 77

Typ	$\Sigma \ell/A(\text{cm}^{-1})$	$\ell_e(\text{cm})$	$A_e(\text{cm}^2)$	$V_e(\text{cm}^3)$	$A_L(\text{nH})\pm 25\%$
FT-23-77	63.8	1.30	0.020	0.027	390
FT-37-77	28.6	2.07	0.072	0.15	880
FT-50-77	22.9	2.95	0.129	0.38	1100
FT-82-77	21.3	5.2	0.243	1.26	1175
FT-114-77	19.8	7.3	0.37	2.70	1275
FT-140-77	11.2	8.9	0.79	7.0	2250
FT-240-77	9.2	14.5	1.58	22.8	2725

16.08.2006