

Datasheet Model LiFePO4 12.8V 18.000mAh

Daniel Beck Mergenthalerallee 77 65760 Eschborn Doc. Version 1.3 01.01.2021

For any questions: Please contact us.

info@theeremit.de 01602614589 www.theeremit.de3

EREMIT is a registered trademark in Germany.

This specification is applied to describe the related battery product in this Specification and the battery/cell supplied by EREMIT.

All cells within this pack are originally produced by Bixell Technology limited. For further informations related to this product please contact us first.

Page 1: Main information
Page 2-3: Cell Characteristics
Page 4: Protection board Data

Page 5: Charge/Discharge notes; Cell Parts

Page 6: Cell Handling Page 7: Warranty

| Number | Description | Ratings | Remarks |
|--------|----------------------|---------------|--------------------------|
| 1; | Nominal Capacity | 18000mAh | At 0,2C CC discharge |
| 2; | Minimal capacity | >18000mAh | |
| 3; | Nominal Voltage | 12.8V | |
| 4; | Delivery voltage | 12.4 V | On delivery |
| 5; | Charge voltage | 14.6V | |
| 6; | Standard Charging | 0.2C Standart | 6 hour nominal |
| | | 1C max. | 1.5 hour rapid |
| 7; | Standard discharging | 1C CC to 8.0V | 18A standard |
| | | 3C max. | 54A max. |
| | | 5C Pulse | Pulse below 1 second. |
| | | | Higher pulse cause the |
| | | | protection to switch off |

| 8; | Pack internal impedance | ≤23mOhm | Measured at 1khz after |
|-----|-------------------------|-------------|------------------------|
| | | | 50% |
| | | | Charge |
| 9; | Operating temperature | 0-45°C | Maximum -10° - 60°C |
| | | Recommended | 10 - 34°C |
| 10; | Internal Chemical | IFR | Lithium-Iron-Phosphate |
| | charact. | | |
| | | | |
| | | | |


10; Long time storage (-5°C – 30°C)

If the battery need be stored for a long time, the voltage should be 13.2V, and stored in the condition as storage proposal. It need at least one charge & discharge cycle every year.

Maximum sizes: 133 x 100 x 84 mm Maximum weight: 1.9 kilogram


Battery Characteristics


| Number | Description | Ratings | Remarks |
|--------|-------------|---|-------------------|
| 1; | Standard | Charging cell initially with constant | |
| | Charge | current at 0.2C to 14.6V, then with | |
| | | constant voltage at 14.6V till charge | |
| | | current is below 0.02C | |
| 2; | Rated | Capacity means the discharge capacity | 18000mAh |
| | capacity | of the cell, which is measured with | |
| | | discharge current of 0.2C with 9.0V | |
| | | cut-off voltage after standard charge. | |
| 3; | Cycle life | Test condition: | >2000 |
| | | Carge 1C to 14.6V -> discharge 1C to | |
| | | 8.0V | |
| | | 80% or more of 1st cycle capacity at | |
| | | 0.5C discharge of operation | |
| 4; | Self | After standard charging stored 1 month | Above 98% |
| | discharge | under storage condition descriped in | residual capacity |
| | | page 2; then measured the capacity with | |
| | | 0.2C till 9.0V | |



Protection circuit Data

| Item | Symbol | Content | Criterion |
|-------------------------|--------------------|--|---|
| Organ ahanga Duataatian | V_{DET1} | Over charge detection voltage | 3.75±0.05V |
| Over charge Protection | tV _{DET1} | Over charge detection delay time | 0.015 ~ 0.14s |
| | V_{REL1} | Over charge release voltage | 3.55±0.05V |
| Over discharge | $V_{ m DET2}$ | Over discharge detection voltage | 2.2±0.1V |
| protection | tV _{DET2} | Over discharge detection delay time | 95 ~ 173ms |
| | V_{REL2} | Over discharge release voltage | 2.5±0.10V |
| | V _{DET3} | Over current detection voltage | N/A |
| Over current protection | I_{DP} | Over current detection current | 100A |
| | tV _{DET3} | Detection delay time | 1~10s |
| | | Release condition | Cut load |
| G1 | | Detection condition | Exterior short circuit |
| Short protection | T _{SHORT} | Detection delay time | 50μs |
| | | Release condition | Cut short circuit |
| Interior resistance | R_{DS} | Main loop electrify resistance | V _C =3.8V; R _{DS} ≤16mΩ |
| Current consumption | I_{DD} | Current consume in normal operation for full board | 25µА Туре 50µА Мах |





2x 4x KIA2803A Mosfet 160A max. Current

Over-Discharge

Short time over discharge does not affect the battery function, but long time over discharges can damage battery performance, and can't use any more. due to its own self-discharge characteristics also lead to over-discharge, to prevent over-discharge occurs, the battery should maintain the certain electric quantity, the cell shall be charged periodically to maintain between 3.0V and 3.65V – in total the pack shall be charged to between 12.0V and 14.6V. Over-discharging may causes loss of cell performance, characteristics, or battery functions.

The electrical products shall be equipped with a device to prevent further discharging exceeding a cut-off voyage specified in the Product Specification.

If Cells below 2.0V

The cell battery pack shall start with a low current (0.02C) for 30 - 45minutes, i.e. pre-charging, before rapid charging starts. The rapid charging shall be started after the (individual) cell voltage has been reached above 2.5V (10V in total) within 30 - 45 minutes that can be determined with the use of an appropriate timer for pre-charging. In case the (individual) cell voltage does not rise to 2.5V (10V in total) within the pre-charging time, then the charger shall have functions to stop further charging and display the cell/pack is at abnormal state.

Charging

Charging current: Do not surpass the largest charging current that specification stipulated.

Charging voltage: Do not surpass the highest limited voltage that specification stipulated.

Charging temperature: within temperature scope that specification stipulated.

Charge with constant current, then with the constant voltage, no reverse charge, which is dangerous



| No. | Part Name | Description | Q'ty | Remark |
|-----|---------------|-----------------------------------|------|--------|
| 1 | Cell/Pack | LiFePo4-12.8V-18000mAh | 1 | |
| 2 | Patterns Tape | Shrink tube, Fibreboard Boxing | 1 | |
| 3 | PCM | JBD-HP045024 8x kia2803A | 1 | |
| 4 | Wire | AWG12 | 2 | |

12. Handling of Cells

12. Warning and cautions in handling the lithium cell

To prevent the possibility of the cell from leaking, heating, explosion, please observe the following precautions:

- 1. ¬ Don't immerse the cell in water.
- 2. ¬ Don't use and leave the cell near a heat source, such as fire or heater.
- 3. ¬ Don't reverse the positive and negative terminals.
- 4. ¬ Don't connect the cell to an electrical outlet directly.
- 5. ¬ Don't discard the cell in fire or heater.
- 6. Don't connect the positive and negative terminal directly with metal objects.
- 7. ¬ Don't transport and store the cell together with metal objects such as necklaces, hairpins.
- 8. ¬ Don't strike, throw or trample the cell.
- 9. ¬ Don't directly solder the cell.
- 10. ¬ Don't pierce the cell with a nail or other sharp object.

¬ Caution

- ¬ If the cell leaks and the electrolyte get into your eyes, don't wipe eyes, instead, thoroughly rinse the eyes with clean running water for at least 15 minutes, and immediately seek medical attention. Otherwise, eye injury can result.
- ¬ If the cell gives off an odor, generates heat, becomes discolored or deformed, or in any way appears
 - abnormal during usage, recharging or storage, immediately remove it from the device or cell charger and stop using it.

Period of Warranty

The period of warranty is 2 year from the date of shipment. Replacement is guaranteed within warranty if battery with defects proven due to manufacturing process instead of the customer's abuse and misuse.

For further warranty regulations please check country-specific regulations made by eremit.

Page 7